

TECHNICAL DATA SHEET – SS-1

DESCRIPTION

Blacklidge's SS-1 is an anionic slow setting asphalt emulsion. Used primarily in the construction of tack coats.

PHYSICAL PROPERTIES

- Boiling Point (°F): 212
- Specific Gravity (H₂O = 1): 1.02
- Solubility in Water: Dispersible
- Appearance and Odor: Brown liquid with Mild Petroleum Odor

| PARAMETER | TEST METHOD | MIN | MAX |
|--------------------------------------|-------------|----------|------|
| Tests on Emulsion | | | |
| Saybolt Furol Viscosity, SFS @ 25 °C | AASHTO T 72 | 20 | 100 |
| Storage Stability, 1 day, % | AASHTO T 59 | ---- | 1.0 |
| Cement Mixing Test, % | AASHTO T 59 | ---- | 2.0 |
| Particle Charge | AASHTO T 59 | Negative | |
| Residue by Distillation | AASHTO T 59 | 57 | ---- |
| Sieve Test | AASHTO T 59 | ---- | 0.1 |
| Tests on Residue | | | |
| Penetration @ 25 °C, dmm | AASHTO T 49 | 100 | 200 |
| Ductility @ 25 °C | AASHTO T 51 | 40 | ---- |
| Solubility, % | AASHTO T 44 | 97.5 | ---- |

LIMITATIONS

Proper storage, handling, and application guidelines must be followed carefully for best results. As with any emulsion, do not allow the material to freeze or boil because of aggressive heating. Freezing or boiling of SS-1 will break the emulsion. SS-1 IS NOT COMPATIBLE WITH CATIONIC EMULSIONS (CRS, CMS, CSS, CQS, etc.). All equipment should be thoroughly cleaned if cationic emulsion was previously present. It is highly recommended for the product to be applied when hot (140°F to 160°F). Please contact your Blacklidge representative prior to first use for detailed storage and handling procedures.

CAUTION

For industrial use only. Refer to SDS for further information.

THIS PRODUCT IS NOT SUBJECT TO THE CONTROLLED PRODUCT REGULATIONS.

The information contained herein is the best information available to Blacklidge relating to our products, the use of our products, and is based on tests believed to be reliable. There is no warranty, EXPRESSED OR IMPLIED in association with this product or its use. Blacklidge assumes no liability for any damages incurred in association with the use of our products, and the liability of Blacklidge will be limited to the replacement of material found to be defective, or, at its option, the refund of the purchase price.

Product information subject to change without notice. © 2016 Blacklidge Emulsions, Inc. All rights reserved.