

BLACKLIDGE[®]

TECHNICAL DATA SHEET – UltraTack™

DESCRIPTION

Blacklidge's UltraTack™ (NTSS-1HM) is the most state of the art anionic emulsion available for high performing, trackless tack coat applications. It is used as a trackless tack coat with excellent bonding properties. It may also be used in prime coat applications where allowed by the Agency.

PHYSICAL PROPERTIES

- Boiling Point (°F): 212
- Specific Gravity (H₂O = 1): 1.03
- Solubility in Water: Dispersible
- Appearance and Odor: Dark Brown liquid with Mild Petroleum Odor

PARAMETER	TEST METHOD	MIN	MAX
Tests on Emulsion			
Saybolt Furol Viscosity, SFS @ 25 °C	ASTM D88	20	100
Storage Stability, 1 day, %	ASTM D244	----	1.0
Residue by Distillation	ASTM D244	50	----
Oil Distillate, %	ASTM D244	----	1.0
Sieve Test	ASTM D244	----	0.3
Tests on Residue			
Penetration @ 25 °C, dmm	ASTM D5	----	20
Softening Point, °C	ASTM D36	65	----
Solubility, %	ASTM D2042	97.5	----
Original DSR @ 82 °C (G*/SIN d, 10 rad/sec)	AASHTO T315	1.0	----

LIMITATIONS

Proper storage, handling, and application guidelines must be followed carefully for best results. As with any emulsion, do not allow the material to freeze or boil because of aggressive heating. Freezing or boiling of UltraTack™ will break the emulsion. UltraTack™ IS NOT COMPATIBLE WITH CATIONIC EMULSIONS (CRS, CMS, CSS, CQS, etc.). All equipment should be thoroughly cleaned if cationic emulsion was previously present. It is highly recommended for the product to be applied when hot (170°F to 180°F). UltraTack™ is applied with conventional distributors. Application rates vary depending on the existing surface, so please consult applicable agency specifications to determine required application rate. Typically these rates are between 0.05 and 0.1 gallons per square yard. In any application even, uniform coverage is critical to achieving the best bond. If the product is to be stored for an extended period of time, the material should be agitated and/or gently circulated prior to use. Please contact your Blacklidge representative prior to first use for detailed storage and handling procedures.

CAUTION

For industrial use only. Refer to SDS for further information.

THIS PRODUCT IS NOT SUBJECT TO THE CONTROLLED PRODUCT REGULATIONS.

The information contained herein is the best information available to Blacklidge relating to our products, the use of our products, and is based on tests believed to be reliable. There is no warranty, EXPRESSED OR IMPLIED in association with this product or its use. Blacklidge assumes no liability for any damages incurred in association with the use of our products, and the liability of Blacklidge will be limited to the replacement of material found to be defective, or, at its option, the refund of the purchase price.

Product information subject to change without notice. © 2016 Blacklidge Emulsions, Inc. All rights reserved.